


IN THE CLAIMS

Claim 1. (Original) A process for dispersing particulate, which comprises mixing an effective dispersing amount of a phosphated triglyceride conforming to the following structure



wherein;

R is selected from the group consisting of $-(\text{CH}_2)_2-$ and $-\text{CH}-\text{CH}-$;

R^1 is $-\text{P}(\text{O})-(\text{OH})_2$;

R^2 and R^3 are independently selected from the group consisting of H and $-\text{P}(\text{O})-(\text{OH})_2$

with a particulate selected from the group consisting of bismuth oxychloride, titanium dioxide, zinc oxide, ferric oxide, ferric titanated mica, fumed silica, spherical silica, polymethylmethacrylate, micronized teflon, boron nitride, acrylate copolymers, aluminum silicate, aluminum starch octenylsuccinate, bentonite, calcium silicate, cellulose, chalk, corn starch, diatomaceous earth, fuller's earth, glyceryl starch, hectorite, hydrated silica, kaolin, magnesium aluminum silicate, magnesium trisilicate, maltodextrin, montmorillonite, microcrystalline cellulose, rice starch, silica, talc, mica, titanium dioxide, zinc laurate, zinc myristate, zinc rosinate, alumina, attapulgite, calcium

carbonate, calcium silicate, dextran, kaolin, nylon, silica silylate, silk powder, sericite, soy flour, tin oxide, titanium hydroxide, trimagnesium phosphate, walnut shell powder, or mixtures thereof and optionally milling, grinding, or homogenizing the mixture.

Claim 2.(Presently Amended) A process of claim 1 wherein [said] the effective dispersing concentration of phosphated [castor] triglyceride ranges from 1 to 50% by weight.

Claim 3. (Original) A process of claim 1 wherein R is $-\text{CH}=\text{CH}-$.

Claim 4. (Original) A process of claim 2 wherein R^2 and R^3 are H.

Claim 5. (Original) A process of claim 2 wherein R^2 is $-\text{P}(\text{O})-(\text{OH})_2$ and R^3 is H.


Claim 6. (Original) A process of claim 3 wherein R^2 and R^3 are both $-\text{P}(\text{O})-(\text{OH})_2$.

Claim 7. (Original) A process of claim 1 wherein R is $-(\text{CH}_2)_2-$.

Claim 8. (Original) A process of claim 7 wherein R^2 and R^3 are H.


Claim 9. (Cancelled) A phosphated compound of claim 7 wherein R^2 and R^3 are both $-\text{P}(\text{O})-(\text{OH})_2$

Claim 10. (Original) A process for dispersing particulate which comprises mixing an effective dispersing amount of a phosphated ester selected from the group consisting of



wherein R is $\text{CH}_3-(\text{CH}_2)_n-$ and n is an integer ranging from 5 to 21;

and



wherein;

R is $-(\text{CH}_2)_n-\text{CH}_3$

R¹ is $-\text{P}(\text{O})-(\text{OH})_2$

n is an integer ranging from 5 to 21;

with a particulate selected from the group consisting of bismuth oxychloride, titanium dioxide, zinc oxide, ferric oxide, ferric titanated mica, fumed silica, spherical silica, polymethylmethacrylate, micronized teflon, boron nitride, acrylate copolymers, aluminum silicate, aluminum starch octenylsuccinate, bentonite, calcium silicate, cellulose, chalk, corn starch, diatomaceous earth, fuller's earth, glyceryl starch, hectorite, hydrated silica, kaolin, magnesium aluminum silicate, magnesium trisilicate, maltodextrin, montmorillonite, microcrystalline cellulose, rice starch, silica, talc, mica, titanium dioxide, zinc laurate, zinc myristate, zinc rosinate, alumina, attapulgit, calcium carbonate, calcium silicate, dextran, kaolin, nylon, silica silylate, silk powder, sericite, soy flour, tin oxide, titanium hydroxide, trimagnesium phosphate, walnut shell powder, or mixtures thereof and optionally milling, grinding, or homogenizing the mixture.